

ACC.	minimale vloeigrens	treksterkte	kerftaaiheid	
CLASSIFICATIE	Reh N/mm ²	Rm N/mm ²	Charpy V (J)	° C
A			-	-
B			27	0
D	235	400-510	27	-20
E			27	-40
AH32			34	0
DH32	315	470-590	34	-20
EH32			34	-40
AH36			34	0
DH36	355	490-620	34	-20
EH36			34	-40